

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-239269

(43)Date of publication of application : 17.09.1993

(51)Int. Cl.
 C08L 21/00
 C08J 3/20
 C08K 3/20
 C08K 3/22
 C08L 21/00
 //(C08L 21/00
 C08L 23:28
 C08L 23:02
 C08L 63:00)

(21)Application number : 04-043652 (71)Applicant : SHOWA DENKO KK

(22)Date of filing : 28.02.1992 (72)Inventor : WATANABE NAOTOSHI
 SAKAE ICHIRO
 HARUO RYOJI
 HAYASHI HIROKI

(54) FLAME-RETARDANT RESIN COMPOSITION AND ITS PRODUCTION

(57)Abstract:

PURPOSE: To produce a flame-retardant thermoplastic elastomer compsn. having high mechanical strengths and being free from bleedout.

CONSTITUTION: 100 pts.wt. polymer component comprising a thermolastic elastomer (A), a chloroethylene polymer (B), and an ethylene polymer (C) is compounded with 10-30 pts. wt. antimony oxide, 10-35 pts.wt. aluminum hydroxide and/or magnesium hydroxide, and 20-50 pts.wt. reaction product of a brominated epoxy compd. with 1,3,5-tribromophenol (having a mol wt. of 1,200-6,000 and a bromine content of 5.0-60wt.%), giving a flame-retardant thermoplastic elastomer compsn. The polymer component contains 80-98wt.% polymer A, and the amt. of polymer B accounts for 10-75wt.% of the total amt. of polymers B and C. All the components except polymer A are premixed, and the resulting premixture is mixed with polymer A.

LEGAL STATUS

[Date of request for examination] 23.10.1998

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3132121

[Date of registration] 24.11.2000

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

BEST AVAILABLE COPY